



## *Adicel ECO-A Series*

- ❖ Excellent dyeing properties- good even buildup, leveling and compatibility with high exhaustion- leading to shorter and more reproducible dyeing on jigs.
- ❖ Higher Wet Fastness than traditionally obtained on acetate fabrics.
- ❖ Good fastness to gas and light and free from catalytic fading.
- ❖ With proper use the ECO-A dyes should result in compliance with the requirements of the Oko-Tex 100 standard (1999 edition), making the dyes suitable for textile articles for retail outlets using this standard.

### **New Jersey Location**

50 Page Road, Clifton, NJ 07012

Phone. 973.778.0122 • Fax. 973.778.1124

### **South Carolina Location**








105 Wood Street, Greenville, SC 29611

Phone. 864.295.1170 • Fax. 864.295.5606



---

[www.greenvillecolorants.com](http://www.greenvillecolorants.com) • Customer Service. 800.832.8985 Fax. 800.763.1001

## Adicel ECO-A Series

Name	Depth %	Secondary Acetate Dyed at 85°C	Co6 A2s			Eo <sub>4</sub>			Go1	Bo2
			CC	CA	PA	CC	CA	PA	1 Cycle 3 Cycles	
Adicel Yellow ECO-A	1.0		5	4-5	4-5	5	4	4	5 5	6 6-7 6-7
Adicel Orange ECO-A	1.0		5	4-5	4-5	5	4	4	5 5	5 6-7 7
Adicel Scarlet ECO-A	1.0		5	4-5	4-5	5	4-5	4	5 5	5-6 6 6
Adicel Crimson ECO-A	1.0		5	4	4	5	4-5	4-5	4-5 4	4-6 4-6 6-7
Adicel Br. Blue ECO-A	1.0		5	4-5	4-5	5	4	4	4-5 4	4 4-5 5
Adicel Navy ECO-A	3.0		5	3-4	3-4	5	3-4	3-4	4-5 4	5 5-6
Adicel Black ECO-A	4.5		5	4	4	5	4	4	4-5 4	4 5

Dyeings removed at:



### **\*\*Disclaimer:**

Seller assumes no obligation or liability, whether in contract, tort, negligence, strict liability or misrepresentation for any advice or assistance given Buyer in relation to the merchandise, such advice or assistance, written or oral, being given without charge and accepted by Buyer's request and at his sole and exclusive risk. Samples will be made available at Buyer's request. Buyers are urged to make their own tests of any product described herein or of any proposed application with respect to which advice or assistance from Seller may be sought.

The fastness properties of the enclosed dyeings are dependent upon the conditions to which they are subjected, and may vary considerably if the dyed fabric is treated with additional chemicals such as fixing or finishing agents. Consequently, the dyed/finished fabric should be tested to assure that the fastness properties meet the necessary requirement. Not all shades can be produced with desired fastness properties. This point should be carefully considered before putting shades into production. The information given is based on work done in our laboratories; consideration should be given to possible variations under local conditions.