



Adicel Series



New Jersey Location

50 Page Road, Clifton, NJ 07012







Phone. 973.778.0122 • Fax. 973.778.1124

South Carolina Location

105 Wood Street, Greenville, SC 29611

Phone. 864.295.1170 • Fax. 864.295.5606


www.greenvillecolorants.com • Customer Service. 800.832.8985 Fax. 800.763.1001

			Washing	Water	Gas Fading	Perspiration		Rubbing		Light	Dry Heat (160°C)
						Acidic	Alkaline	Dry	Wet		
Adicel Yellow G Disperse Yellow 3	1.5%		4	4-5	4	4	4	4	4	5	4-5
Adicel Orange GR Disperse Orange 3	1.5%		3-4	4	4	4	4	4	4	5-6	4-5
Adicel Scarlet B Disperse Red 1	1.5%		4	4-5	4	3-4	3-4	3-4	3-4	4-5	4-5
Adicel Blue BNG Disperse Blue 3	1.5%		4	5	2-3	4	4	4	4	4	4-5
Adicel Black EHG Disperse Black	4.0%		3-4	4-5	3	3	3	4	4	4-5	4-5
Adicel Black BB Disperse Black	4.0%		4	5	3-4	4	4	4	4	6	4-5

Dyeing Method

Exhaust Dyeing on Acetate


Adicel Colors: X%
Dyebath pH: 4.5-5
Acetic Acid: 0.25g/l
Sodium Acetate: 1g/l



Dyes & Agent

Exhaust Dyeing on Nylon

Adicel Colors: X%
Dyebath pH: 4.5-5
Acetic Acid: 0.25g/l
Sodium Acetate: 1g/l



Dyes & Agent

Fastness Test:

Washing: ISO 105-C03
Perspiration: ISO 105-E04
Dry Heat: ISO 105-P01
Rubbing: ISO 105-X12
Light: ISO 105-B02
Water: ISO 405-E01
Gas Fading: JIS L0855 (Nitrogen Oxide)

pH Range:

pH2: Sulfuric Acid + Acetic Acid
pH3: Acetic Acid
pH4-6: Acetic Acid + Sodium Acetate
pH7: Primary Sodium phosphate + Secondary Sodium Phosphate
pH8-10: Sodium Carbonate + Sodium Bicarbonate
pH 10-11: Sodium Hydroxide + Sodium Carbonate

Disclaimer:

Seller assumes no obligation or liability, whether in contract, tort, negligence, strict liability or misrepresentation for any advice or assistance given Buyer in relation to the merchandise, such advice or assistance, written or oral, being given without charge and accepted by Buyer's request and at his sole and exclusive risk. Samples will be made available at Buyer's request. Buyers are urged to make their own tests of any product described herein or of any proposed application with respect to which advice or assistance from Seller may be sought.