



Adicryl AD Series

New Jersey Location

50 Page Road, Clifton, NJ 07012












Phone. 973.778.0122 • Fax. 973.778.1124

South Carolina Location

105 Wood Street, Greenville, SC 29611

Phone. 864.295.1170 • Fax. 864.295.5606

www.greenvillecolorants.com • Customer Service. 800.832.8985 Fax. 800.763.1001

					Staining				Washing		Rubbing		Light (82H)		Perspiration		Heat Setting			
					F Value 0.12	Dyeing Speed 3-4	PH Stability 3-5	PES	Cotton	Wool	Nylon	AATCC 2A	ISO 105-C03	Dry	Wet	0.5%	2.0%	Alkali	Acid	180°Cx60°
								4-5	5	5	4-5	5	5	5	5	3	4	5	5	4-5
	Adicryl Br. Flavine AD-10G	2%																		
	Adicryl Yellow AD-3GS	2%	0.32	3-4	3-7	5	5	4-5	4-5	5	5	5	5	6	6-7	5	5	5		
	Adicryl Yellow AD-3RL	2%	0.22	3	3-6	5	4-5	4-5	4	5	5	5	5	6	6-7	5	5	5		
	Adicryl Yellow AD-GL	2%	0.22	3	3-6	5	5	4	4-5	5	5	5	5	6	6-7	5	5	5		
	Adicryl Red AD-GRL	2%	0.23	3-4	3-5	4	4-5	4	4-5	5	5	5	5	5	6	5	5	4-5		
	Adicryl Red AD-GL	2%	0.23	3	3-6	4-5	4-5	3-4	3-4	5	5	5	5	5	6	5	5	4-5		
	Adicryl Blue AD-GSLN	2%	0.22	2-3	3-4.5	5	4-5	4-5	4-5	5	5	5	5	5	5	5	5	5		
	Adicryl Navy AD-PRN	2%	0.23	3	3-4.5	4-5	4-5	4-5	4-5	5	5	5	5	4-5	4-5	5	5	5		
	Adicryl Blue AD-BG	2%	0.22	3	3-5.5	4-5	5	4	4	5	5	5	5	5	6	5	5	4-5		
	Adicryl Blue AD-BSF	2%	0.24	3	3-5.5	5	5	4-5	4-5	5	5	5	5	5	6	5	5	5		
	Adicryl Black AD-RN	2%	0.24	3	3-4.5	4	4-5	4	1-2	5	5	5	5	5	5-6	5	5	5		

**Disclaimer:

Seller assumes no obligation or liability, whether in contract, tort, negligence, strict liability or misrepresentation for any advice or assistance given Buyer in relation to the merchandise, such advice or assistance, written or oral, being given without charge and accepted by Buyer's request and at his sole and exclusive risk. Samples will be made available at Buyer's request. Buyers are urged to make their own tests of any product described herein or of any proposed application with respect to which advice or assistance from Seller may be sought.

The fastness properties of the enclosed dyeings are dependent upon the conditions to which they are subjected, and may vary considerably if the dyed fabric is treated with additional chemicals such as fixing or finishing agents. Consequently, the dyed/finished fabric should be tested to assure that the fastness properties meet the necessary requirement. Not all shades can be produced with desired fastness properties. This point should be carefully considered before putting shades into production. The information given is based on work done in our laboratories; consideration should be given to possible variations under local conditions.