



## *Adicryl Series*

### **New Jersey Location**

50 Page Road, Clifton, NJ 07012

Phone. 973.778.0122 • Fax. 973.778.1124

### **South Carolina Location**

105 Wood Street, Greenville, SC 29611

Phone. 864.295.1170 • Fax. 864.295.5606

---

[www.greenvillecolorants.com](http://www.greenvillecolorants.com) • Customer Service. 800.832.8985 Fax. 800.763.1001



# Greenville Colorants

	Dye Name	Xenon FadeOmeter		Wash Test #3A		Water Bleed		Dry Clean Alt.	Perspiration Orlon		Crock Test		Artificial Light	Solubility Hot	K Value
		Light	Heavy	Alt	Stain	Alt.	Stain		Alt	Stain	Wet	Dry			
	2% Adicryl Yellow L Basic Yellow 13	5-6	7-8	5	5	4	5	5	5	5	5	5	R	6	3.5
	1% Adicryl Yellow 9GL 200% Basic Yellow 21	5	6-7	4	5	4	5	5	4-5	5	5	4-5	R	2	2.5
	2% Adicryl Yellow 4GN-T Basic Yellow 51	6-7	7-8	4	5	5	5	4	5	5	5	5	R	7	2.5
	1% Adicryl Yellow R 200% Basic Yellow 11	5	7-8	5	5	4-5	5	5	4-5	5	5	5	R	3	3.0
	1% Adicryl Yellow 6DL 200% Basic Yellow 29	4-5	6-7	4	5	5	5	3	4-5	5	5	5	r	5	2.0
	1% Adicryl G. Yellow GL 200% Basic Yellow 28	5	6-7	4-5	5	4	5	3	5	5	5	5	R	3	3.0
	1% Adicryl Orange G 200% Basic Orange 21	4	6	4-5	4-5	5	5	4-5	5	5	5	5	Y	2	1.5
	2% Adicryl Red GL Basic Red 18	5-6	7	4	4-5	4-5	5	4-5	5	5	5	5	Y-D	7	2.5
	4% Adicryl Red GBL Basic Red 104	5	6-7	5	5	4	5	5	5	5	5	5	Y-Br.	5	3.0
	1% Adicryl Red GRL Basic Red 46	4-5	6-7	4-5	5	5	4-5	4	5	4-5	5	5	Y-Br.	2	3.0
	2% Adicryl Br. Red 4G 200% Basic Red 14	3	4-5	4-5	4-5	4	5	4-5	5	5	5	5	Y-Br	2	3.0
	2% Adicryl Br. Pink GN-T Basic Red 27	1-2	2-3	4-5	5	4-5	5	4-5	5	5	5	5	Y	5	3.0
	2% Adicryl Br. Red GBNT Basic Violet 39	2	3-4	4	5	4	4-5	4	5	5	5	5	Y	7	2.5
	1% Adicryl Br. Red 2B 200% Basic Violet 16	2	3	4-5	5	4-5	5	5	5	5	5	5	Y-Br	2	2.0
	2% Adicryl Blue BCR Basic Blue 21	5	6-7	4-5	5	4	5	4-5	5	5	5	5	R	5	2.5
	2% Adicryl Fast Blue GLK Basic Blue 54	5	6-7	4	5	5	5	4	5	5	5	5	R	5	0.5
	2% Adicryl Blue GRLA Basic Blue 41	4-5	6-7	5	5	5	5	4-5	5	5	5	5	R	5	2.0
	1% Adicryl Blue ER 200% Basic Blue 77	4	5-6	4	5	4	5	4-4	4-5	4	5	5	R	5	4.0
	1% Adicryl Blue 5G 200% Basic Blue 5	3	4-5	5	5	4	5	5	4	5	5	5	G	3	3.5
	3% Adicryl Black PSR Basic Black	-	5	4	4-5	4-5	5	4-5		5	5	5	Y	1	-

<u>Abbreviations</u>		<u>Solubility Group</u>	<u>Solubility Range</u>	<u>Xenon Ratings</u>	
Y	Yellow	1	<10	1	<5 Hours
O	Orange	2	11-20	2	5 Hours
R	Red	3	21-30	3	10 Hours
V	Violet	4	31-40	4	20 Hours
B	Blue	5	41-50	5	40 Hours
G	Green	6	51-75	6	80 Hours
D	Duller	7	76-100	7	160 Hours
BR	Brighter	8	101-150	8	320 Hours

## **\*\*Disclaimer:**

Seller assumes no obligation or liability, whether in contract, tort, negligence, strict liability or misrepresentation for any advice or assistance given Buyer in relation to the merchandise, such advice or assistance, written or oral, being given without charge and accepted by Buyer's request and at his sole and exclusive risk. Samples will be made available at Buyer's request. Buyers are urged to make their own tests of any product described herein or of any proposed application with respect to which advice or assistance from Seller may be sought.

The fastness properties of the enclosed dyeings are dependent upon the conditions to which they are subjected, and may vary considerably if the dyed fabric is treated with additional chemicals such as fixing or finishing agents.

Consequently, the dyed/finished fabric should be tested to assure that the fastness properties meet the necessary requirement. Not all shades can be produced with desired fastness properties. This point should be carefully considered before putting shades into production. The information given is based on work done in our laboratories; consideration should be given to possible variations under local conditions.

