



Adivat Paste Dyes



New Jersey Location

50 Page Road, Clifton, NJ 07012

Phone. 973.778.0122 • Fax. 973.778.1124

South Carolina Location

105 Wood Street, Greenville, SC 29611

Phone. 864.295.1170 • Fax. 864.295.5606

www.greenvillecolorants.com • Customer Service. 800.832.8985 Fax. 800.763.1001



Greenville Colorants

g/l	Dye Name	Physical Properties	Usage						Fastness						
			Substrate		Method			Leveling	Light		Washing		Dry Cleaning		
			100% Cotton	Cotton/Poly	Cont.	Exh.	Print		Pale	Dark	Shade Change	Cotton Stain	Chlorine Bleach	Shade Change	Cotton Stain
30	Adivat Yellow Brown D Vat Yellow 1	Double Paste	X	X	X	X	X	E	5	6	5	5	5	4-5	4-5
30	Adivat Supra Yellow GC Vat Yellow 2	Paste	X	X	X	X	X	G	3	4-5	5	5	5	4-5	5
15	Adivat Supra Flavine PCT Vat Yellow 2	Double Paste	X	X	X	X	X	G	3	4-5	5	5	5	4-5	5
30	Adivat Yellow 3GL Vat Yellow 33	Paste	X	X	X	X	X	E	6	7	4-5	5	5	4-5	5
30	Adivat Yellow PGY Vat Yellow	Paste	X	X	X	X	X	G	3-4	5	5	5	5	4-5	5
45	Adivat Orange RRT New Vat Orange 2(s)	Paste	X	X	X	X	X	G	6	7	4-5	4-5	4-5	4-5	4-5
30	Adivat Red 3B Vat Red	Double Paste	X	X	X	X	X	E	6-7	7-8	5	5	5	4-5	4-5
45	Adivat Bordeaux RR Vat Red 15	Double Paste	X	X	X	X	X	VG	6	7	4-5	4-5	4-5	3-4	4
45	Adivat Violet 4R-BS Vat Violet 1	Double Paste	X	-	X	X	X	M	5-6	7-8	4-5	5	4-5	5	3-4
45	Adivat Violet B Vat Violet 13	Double Paste	X	X	X	X	X	VG	6	7	4-5	5	4-5	5	3-4
45	Adivat Brown BR Vat Brown 1	Paste	X	X	X	X	X	VG	7	8	4-5	5	5	5	5
45	Adivat Red Brown RF Vat Brown 11(s)	Paste	X	X	X	X	X	VG	6-7	7-8	4-5	5	5	4-5	5
-	Adivat Brown HRR Vat Brown 57	Paste	X	-	-	-	X	G	7	7-8	4-5	4-5	4-5	4-5	4-5
30	Adivat Brown GSN Vat Brown	Paste	X	X	X	X	X	E	6-7	7-8	4-5	4-5	4-5	4-5	5
30	Adivat Yellow Brown 3MY Vat Brown	Paste	X	X	X	-	-	VG	6	7-8	4-5	4-5	4-5	4	4-5
37.5	Adivat Supra Jade Green Vat Green 1	Double Paste	X	X	X	X	X	VG	6	7-8	4-5	5	4-5	4-5	4
37.5	Adivat Jade FFB Vat Green 1	Double Paste	X	X	X	X	X	VG	6	7-8	4-5	5	4-5	4-5	4
45	Adivat Green B Vat Green 3	Paste	X	X	X	X	X	M	7-8	8	4-5	5	4-5	4-5	5
22.5	Adivat Olive Green 2B Vat Green 3	Double Paste	X	X	X	X	X	M	7-8	8	4-5	5	4-5	4-5	5
22.5	Adivat Green LM Vat Green 3	Double Paste	X	X	X	X	X	M	7-8	8	4-5	5	4-5	4-5	5
30	Adivat Tan 2G Vat Green 8	Paste	X	X	X	-	-	G	6-7	7-8	4-5	5	4-5	4-5	4-5
45	Adivat Green GTP Vat Green	Paste	X	X	X	X	X	M	6-7	7-8	4-5	4-5	4-5	4-5	5



g/l	Dye Name	Physical Properties	Usage						Fastness						
			Substrate		Method			Leveling	Light		Washing		Dry Cleaning		
			100% Cotton	Cotton/ Poly	Cont.	Exh.	Print		Pale	Dark	Shade Change	Cotton Stain	Chlorine Bleach	Shade Change	Cotton Stain
30	Adivat Olive T Vat Black 25	Paste	X	X	X	X	X	G	7-8	8	5	5	4	4-5	4-5
30	Adivat Olive R Vat Black 25	Double Paste	X	X	X	X	-	E	6-7	7-8	4-5	4-5	4-5	4	5
-	Adivat Olive S Vat Black	Paste	X	X	X	X	-	G	7-8	8	5	5	4	4-5	4-5
-	Adivat Blue RS Vat Blue 4	-	-	-	-	-	-	-	-	-	-	-	-	-	-
30	Adivat Blue BF Vat Blue 6	Double Paste	X	X	X	X		G	7	7-8	4-5	5	3-4	4-5	5
-	Adivat Dark Blue BOA Vat Blue 20	Paste	X	-	X	X	X	M	5-6	7	3	4-5	4-5	4	3
-	Adivat Blue N Vat Blue 43	Paste	X	X	X	X	-	VG	3	5-6	4	4	2-3	4-5	5
60	Adivat Br. Blue D Vat Blue	50% Paste	X	X	X	-	-	G	7	7-8	4-5	5	3-4	4-5	5
90	Adivat Navy K Vat Blue	Paste	X	X	X	X	X	G	6-7	7-8	4-5	5	4-5	4-5	4
45	Adivat Navy Blue 2B Vat Blue	Paste	X	-	X	X	X	M	6	7	3-4	4-5	4-5	4	34
30	Adivat Grey G2R Vat Black 22(s)	Double Paste	X	X	X	X	X	M	6-7	7-8	4-5	4-5	4	4-5	5
30	Adivat Grey 2GL Vat Black	Double Paste	X	X	X	X	X	G	7	8	4-5	5	4-5	4-5	5
30	Adivat Grey GS Vat Black	Double Paste	X	X	X	X		G	6-7	7-8	4-5	5	4-5	4-5	5
22.5	Adivat Direct Black SW Vat Black 16	Double Paste	X	X	X	X	X	M	6	7	4	4	4	4-5	5
22.5	Adivat Black EP New Vat Black	Double Paste	X	X	X	X	X	G	-	7	4-5	4-5	4	4	4

****Disclaimer:**

Seller assumes no obligation or liability, whether in contract, tort, negligence, strict liability or misrepresentation for any advice or assistance given Buyer in relation to the merchandise, such advice or assistance, written or oral, being given without charge and accepted by Buyer's request and at his sole and exclusive risk. Samples will be made available at Buyer's request. Buyers are urged to make their own tests of any product described herein or of any proposed application with respect to which advice or assistance from Seller may be sought.

The fastness properties of the enclosed dyeings are dependent upon the conditions to which they are subjected, and may vary considerably if the dyed fabric is treated with additional chemicals such as fixing or finishing agents. Consequently, the dyed/finished fabric should be tested to assure that the fastness properties meet the necessary requirement. Not all shades can be produced with desired fastness properties. This point should be carefully considered before putting shades into production. The information given is based on work done in our laboratories; consideration should be given to possible variations under local conditions.